



Standard Specification for Copper-Base Alloy Continuous Castings¹

This standard is issued under the fixed designation B 505; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope *

1.1 This specification establishes requirements for continuously cast rod, bar, tube, and shapes produced from copperbase alloys with nominal compositions as listed in Table 1.²

1.2 The values stated in inch-pound units are the standard. SI values given in parentheses are provided for information purposes only.

2. Referenced Documents

2.1 The following documents in the current issue of the Book of Standards form a part of this specification to the extent referenced herein:

2.2 *ASTM Standards:*

B 208 Practice for Preparing Tension Test Specimens for Copper-Base Alloys for Sand, Permanent Mold, Centrifugal and Continuous Castings³

B 824 Specification for General Requirements for Copper Alloy Castings³

E 8 Test Methods for Tension Testing of Metallic Materials⁴

E 10 Test Method for Brinell Hardness of Metallic Materials⁴

E 18 Test Methods for Rockwell Hardness and Rockwell Superficial Hardness of Metallic Materials⁴

E 527 Practice for Numbering Metals and Alloys (UNS)⁵

3. Ordering Information

3.1 Orders for continuous castings under this specification should include the following information:

3.1.1 Specification title, number, and year of issue,

3.1.2 Quantity, dimensions, and temper,

3.1.3 Copper Alloy UNS Number,

3.1.4 Tolerances, if different from Section 8 and Tables 2-8,

3.1.5 *ASME Boiler and Pressure Vessel Code*⁶ requirements (Section 7),

3.1.6 When castings are purchased for agencies of the U.S. Government, the Supplementary Requirements of Specification B 824 may be specified.

3.2 The following requirements are optional and should be specified in the purchase order when required.

3.2.1 Chemical analysis of residual elements (Section 5),

3.2.2 Mechanical requirements, (Section 6),

3.2.3 Witness inspection (Specification B 824),

3.2.4 Certification (Specification B 824),

3.2.5 Foundry test report (Specification B 824),

3.2.6 Product marking (Specification B 824),

3.2.7 Castings for seawater service (Section 4),

3.2.8 Approval of weld repair and records of repair (Section 9).

4. Materials and Manufacture

4.1 For better corrosion resistance in sea water applications, castings in Copper Alloy C95800 shall be given a temperature anneal heat treatment at $1250 \pm 50^\circ\text{F}$ ($675 \pm 10^\circ\text{C}$) for 6 h minimum. Cooling shall be by the fastest means possible that will not cause excessive distortion or cracking. Propeller castings shall be exempt from this requirement.

4.2 Copper Alloy UNS Nos. C95300, C95400, C95410, and C95500 may be supplied in the heat-treated condition to obtain the higher mechanical properties shown in Table 9. Suggested heat treatments for these alloys and Copper Alloy UNS No. C95520 are given in Table 2. Actual practice may vary by manufacturer.

4.3 Copper Alloy UNS No. C95520 is used only in the quench-hardened and tempered (TQ30) condition.

4.4 Copper Alloy UNS No. C96900 is normally supplied heat treated at 1520°F (825°C) for 1 h followed by a water quench, then aged at 800°F (425°C) for 4 h followed by a water quench.

4.5 If test bar coupons representing castings made in Copper Alloy UNS Nos. C94700HT, C95300HT, C95400HT, C95410HT, C95500HT, C95520HT, C95800 temper annealed, C95900 annealed and C96900 are removed from the continuous castings before heat treatment, the coupons shall be heat

¹ This specification is under the jurisdiction of ASTM Committee B-5 on Copper and Copper Alloys and is the direct responsibility of Subcommittee B05.05 on Castings and Ingots for Remelting.

Current edition approved Sept. 10, 1996. Published November 1996. Originally published as B 505 – 70. Last previous edition B 505 – 95.

² The UNS system for copper and copper alloys (see Practice E 527) is a simple expansion of the former standard designation system accomplished by the addition of a prefix “C” and a suffix “00”. The suffix can be used to accommodate composition variations of the base alloy.

³ *Annual Book of ASTM Standards*, Vol 02.01.

⁴ *Annual Book of ASTM Standards*, Vol 03.01.

⁵ *Annual Book of ASTM Standards*, Vol 01.01.

⁶ Available from the American Society of Mechanical Engineers, United Engineering Center, 345 East 47th St., New York, NY 10017.

TABLE 1 Nominal Composition

Copper Alloy UNS No.	Designation	Composition, %							
		Copper	Tin	Lead	Zinc	Nickel	Aluminum	Iron	Manganese
C83600	lead red brass	85	5	5	5
C83800	lead red brass	83	4	6	7
C84200	lead semi-red brass	80	5	2	13
C84400	lead semi-red brass	81	3	7	9
C84800	lead semi-red brass	76	3	6	15
C85700	lead naval brass	61	1	1	37
C86200	high-strength yellow brass	66	23	...	5	3	3
C86300	high-strength yellow brass	62	26	...	6	3	3
C86500	high-strength yellow brass	58	39	...	1	1	1
C89320 ^A	bismuth tin bronze	89	6
C90300	tin bronze	88	8	...	4
C90500	tin bronze	88	10	...	2
C90700	tin bronze	89	11
C91000	tin bronze	85	15
C91300	tin bronze	81	19
C92200	lead tin bronze	88	6	2	4
C92300	lead tin bronze	87	8	1	4
C92500	nickel-phosphor bronze	86.5	11	1	...	1.5
C92700	lead tin bronze	88	10	2
C92800	lead tin bronze	79	16	5
C92900	lead nickel-tin bronze	84	10	2.5	...	3.5
C93200	high-lead tin bronze	83	7	7	3
C93400	high-lead tin bronze	84	8	8
C93500	high-lead tin bronze	85	5	9	1
C93600	high-lead tin bronze	81	7	12
C93700	high-lead tin bronze	80	10	10
C93800	high-lead tin bronze	78	7	15
C93900	high-lead tin bronze	78	6	16
C94000	high-lead tin bronze	72	13	15
C94100	high-lead tin bronze	75	5	20
C94300	high-lead tin bronze	70	5	25
C94700	nickel-tin bronze	88	5	0	2	5
C94800	lead nickel-tin bronze	87	5	1	2	5
C95200	aluminum bronze	88	9	3	...
C95300	aluminum bronze	89	10	1	...
C95400	aluminum bronze	85	11	4	...
C95410	aluminum bronze	84	2	10	4	...
C95500	nickel-aluminum bronze	81	4	11	4	...
C95520	nickel-aluminum bronze	78.5	5.5	11	5.0	...
C95700	manganese nickel aluminum bronze	75	2	8	3	12
C95800	nickel-aluminum bronze	81.3	4.5	9	4	1.2
C95900	aluminum bronze	82.5	13	4.5	...
C96400	copper-nickel	70	30
C96900	copper-nickel	76.6	8	15	0.4
C97300	lead nickel bronze	57	2	9	20	12
C97600	lead nickel bronze	64	4	4	8	20
C97800	lead nickel bronze	66	5	2	2	25
C99500 ^B	special alloy	87	1.5	4.5	1.7	4.0	...

^A Bismuth 5.0

^B Silicon 1.3

TABLE 2 Suggested Heat Treatments

Copper Alloy UNS No.	Solution Treatment (not less than 1 h followed by water quench), °F(°C)	Annealing Treatment (not less than 2 h followed by air cool), °F(°C)
C95300	1585–1635 (860–890)	1150–1225 (620–660)
C95400, C95410, C95500	1600–1675 (870–910)	1150–1225 (620–660)
C95520	(2 h followed by water quench) 1600–1700 (870–925)	925–1000 (495–540)

TABLE 3 Finishing Allowances for Tube (Round Only)

Finished Outside Diameter, in. (mm)	Finish Allowances Added to Finished or Print Dimensions of the Part, in. (mm)	
	Inside Diameter	Outside Diameter
Up to 4 (102), excl	–0.031 (–0.79)	+ 0.031 (0.79)
4 (102)–5 (127), incl	–0.063 (–1.6)	+ 0.063 (1.6)
Over 5 (127)	–0.094 (–2.4)	+ 0.094 (2.4)
Copper Alloy UNS Nos. C86200, C86300, C86500, C95200, C95300, C95400, C95500, C95800, C95900, and C96400		
Up to 3 (76.2), incl	–0.125 (–3.2)	+ 0.063 (1.6)
Over 3 (76.2)–4 (102), incl	–0.125 (–3.2)	+ 0.094 (2.4)
Over 4 (102)–5½ (140), incl	–0.188 (–4.8)	+ 0.125 (3.2)
Over 5½ (140)	–0.250 (–6.4)	+ 0.188 (4.8)

treated with the continuous castings.

5. Chemical Composition

5.1 The continuous castings shall conform to the require-

ments for major elements shown in Table 10.

5.2 These specification limits do not preclude the presence of other elements. Limits may be established and analysis

TABLE 4 Finishing Allowances for Rod and Bar

Finished Outside Diameter or Distance Between Parallel Surfaces, in. (mm)	Rounds		Squares, Rectangles, Hexagons, Octagons
	Tolerances, Plus ^A and Minus, ^A in. (mm)		
All Alloys Except as Noted Below			
Up to 4 (102), excl	+ 0.031 (0.79)	+ 0.031 (0.79)	
4 (102)–5 (127), incl	+ 0.063 (1.6)	+ 0.063 (1.6)	
Over 5 (127)	+ 0.094 (2.4)	+ 0.094 (2.4)	
Copper Alloy UNS Nos. C86200, C86300, C86500, C95200, C95300, C95400, C95500, C95800, C95900, C96400			
Up to 3 (76.2), incl	+ 0.0625 (1.6)	+ 0.0625 (1.6)	
Over 3 (76.2)–4 (102), incl	+ 0.093 (2.4)	+ 0.0625 (1.6)	
Over 4 (102)–5½ (140), incl	+ 0.125 (3.2)	+ 0.0625 (1.6)	
Over 5½ (140)	+ 0.188 (4.8)	+ 0.0625 (1.6)	

TABLE 5 Diameter Tolerances for Rod and Bar

Diameter or Distance Between Parallel Surfaces, in. (mm)	Tolerances, Plus ^A and Minus, ^A in. (mm)	
	Rounds	Squares, Rectangles, Hexagons, Octagons
All Alloys Except as Noted Below		
Up to 4 (102), excl	0.005 (0.13)	0.016 (0.41)
4 (102)–5 (127), incl	0.008 (0.20)	0.016 (0.41)
Over 5 (127)	0.016 (0.41)	0.016 (0.41)
Copper Alloy UNS Nos. C86200, C86300, C86500, C95200, C95300, C95400, C95500, C95800, C95900, and C96400		
Up to 3 (76.2), incl	0.010 (0.25)	0.020 (0.51)
Over 3 (76.2)–4 (102), incl	0.015 (0.38)	0.020 (0.51)
Over 4 (102)–5½ (140), incl	0.020 (0.51)	0.020 (0.51)
Over 5½ (140)	0.025 (0.64)	0.025 (0.64)

^AWhen tolerances are specified as all plus or all minus, double the values given.

TABLE 6 Diameter Tolerances for Tube (Round Only)

Average Outside Diameter, in. (mm)	Tolerances, in. (mm)		
	Outside Diameter	Inside Diameter	
		Plus ^A or Minus ^A	Plus ^B
All Alloys Except as Noted Below			
Up to 4 (102), excl	0.005 (0.13)	0.012 (0.30)	0.033 (0.84)
4 (102)–5 (127), incl	0.008 (0.20)	0.016 (0.41)	0.046 (1.2)
Over 5 (127)	0.016 (0.41)	0.032 (0.81)	0.064 (1.6)
Copper Alloy UNS Nos. C86200, C86300, C86500, C95200, C95300, C95400, C95500, C95800, C95900, and C96400			
Up to 3 (76), incl	0.010 (0.25)	0.012 (0.32)	0.033 (0.84)
Over 3 (76)–4 (102), incl	0.015 (0.38)	0.015 (0.38)	0.050 (1.3)
Over 4 (102)–5½ (140), incl	0.020 (0.51)	0.025 (0.64)	0.070 (1.8)
Over 5½ (140)	0.025 (0.64)	0.035 (0.86)	0.090 (2.3)

^AWhen tolerances are specified as all plus or all minus double the values given.

^BWhen tolerances are specified as all plus or all minus, total the values given.

required for unnamed elements agreed upon between the manufacturer or supplier and the purchaser. Copper or zinc may be given as remainder and may be taken as the difference between the sum of all elements analyzed and 100 %. When all named elements in Table 10 are analyzed, their sum shall be as specified in Table 11.

5.3 It is recognized that residual elements may be present in cast copper-base alloys. Analysis shall be made for residual elements only when specified in the purchase order.

6. Mechanical Properties

6.1 Reference should be made to Table 9 for minimum mechanical requirements.

6.2 Mechanical tests are required only when specified by the purchaser in the purchase order.

TABLE 7 Roundness Tolerances

Outside Diameter, in. (mm)	Maximum Out-of-Roundness, ^A in. (mm)
Up to 4 (102), excl	0.020 (0.51)
4 (102)–5 (127), incl	0.032 (0.81)
Over 5 (127)	0.064 (1.6)
Copper Alloy UNS Nos. C86200, C86300, C86500, C95200, C95300, C95400, C95500, C95800, C95900, and C96400	
Up to 3 (76.2), incl	0.025 (0.64)
Over 3 (76.2)–4 (102), incl	0.040 (1.0)
Over 4 (102)–5½ (140), incl	0.060 (1.5)
Over 5½ (140)	0.075 (1.9)

^AThe deviation from roundness is measured as the difference between major and minor diameters as determined at any one cross section of the tube.

TABLE 8 Tolerances for Shapes

Outside Dimension, ^A in. (mm)		Inside Dimension, ^B in. (mm)	
All Alloys Except as Noted Below			
Plus	Minus	Plus	Minus
0.016 (0.41)	0.016 (0.41)	0.032 (0.81)	0.064 (1.6)
Copper Alloy UNS Nos. C86200, C86300, C86500, C95200, C95300, C95400, C95500, C95800, C95900, and C96400			

Dimensional tolerances for all other shapes (not covered by 4.1 or 4.2) shall be subject to agreement between purchaser and manufacturer.

^AWhen tolerances are specified as all plus or all minus, double the values given.

^BWhen tolerances are specified as all plus or all minus, total the values given.

6.3 Exceptions to mechanical property requirements may be taken in the case of small diameter solids or castings having section thicknesses less than the ½-in. (12.7-mm) diameter nominal size of the standard tension test specimen. In these cases, mechanical property requirements shall be subject to agreement between the purchaser and the manufacturer. For suggested dimensions of subsize test bars see Test Methods E 8.

7. ASME Requirements

7.1 When specified in the purchase order to meet *ASME Boiler and Pressure Vessel Code* requirements, continuous castings shall comply with the following:

7.1.1 Certification requirements of Specification B 824.

7.1.2 Foundry test report requirements of Specification B 824.

7.1.3 Continuous castings shall be marked with the manufacturer's name, the Copper Alloy UNS No., and the casting quality factor. In addition, heat numbers, or serial numbers that are traceable to heat numbers, shall be marked on all pressure-containing castings individually weighing 50 lb. (22.7 kg) or more. Pressure-containing castings weighing less than 50 lb. (22.7 kg.) shall be marked with either the heat number or a serial number that will identify the casting as to the month in which it was poured. Marking shall be in such a position as not to injure the usefulness of the casting.

7.1.4 When Copper Alloy UNS No. C95200 is specified to meet *ASME Boiler and Pressure Vessel Code* requirements a sample from each 2000-lb interval or continuous casting shall be tested. Each continuous casting from which the test bar was taken shall be identified should retesting be required. If all of the test bars from the initial sampling meet the requirements the lot shall be acceptable. The fractured bars shall be retained for chemical verification.

TABLE 9 Mechanical Requirements

Copper Alloy UNS No.	Tensile Strength, min ^A		Yield Strength, at 0.5 % Extension Under Load, min ^A		Elongation in 2 in. or 50 mm, min, %	Brinell Hardness, min	Remarks
	ksi ^B	MPa ^C	ksi ^B	MPa ^C			
C83600	36	248	19	131	15		
C83800	30	207	15	97	16		
C84200	32	221	16	110	13		
C84400	30	207	15	103	16		
C84800	30	207	15	103	16		
C85700	40	276	14	97	15		
C86200	90	621	45	310	18		
C86300	110	758	62	427	14		
C86500	70	483	25	172	25		
C89320	35	241	18	124	15		
C90300	44	303	22	152	18		
C90500	44	303	25	172	10		
C90700	40	276	25	172	10		
C91000	30	207	160 (3000 kg)	
C91300		
C92200	38	262	19	131	18		
C92300	40	276	19	131	16		
C92500	40	276	24	165	10		
C92700	38	252	20	138	8	...	Rockwell B 72–82
C92800		
C92900	45	310	25	172	8		
C93200	35	241	20	138	10		
C93400	34	234	20	138	8		
C93500	30	207	16	110	12		
C93600	33	227	20	138	10		
C93700	35	241	20	138	6		
C93800	25	172	16	110	5		
C93900	25	172	16	110	5		
C94000	80 (500 kg)	
C94100	25	172	17	117	7		
C94300	21	145	15	103	7		
C94700	45	310	20	138	25		
C94700HT	75	517	50	345	5		heat treated
C94800	40	276	20	138	20		
C95200	68	469	26	179	20		
C95300	70	483	26	179	25		
C95300HT	80	552	40	276	12		heat treated
C95400	85	586	32	221	12		
C95400HT	95	655	45	310	10		heat treated
C95410	85	586	32	221	12		
C95410HT	95	655	45	310	10		heat treated
C95500	95	655	42	290	10		
C95500HT	110	758	62	427	8		heat treated
C95520HT	125	862	95 ^D	655 ^D	2	262 (3000 kg)	heat treated ^E
C95700	90	620	40	275	15		
C95800 ^F	85	586	35	241	18		
C95900	241 (3000 kg)	
C96400	65	448	35	241	25		
C96900HT	110	758	105 ^D	724 ^D	4		Rockwell C32
C97300	30	207	15	103	8		
C97600	40	276	20	138	10		
C97800	45	310	22	152	8		
C99500	70	483	40	276	12		

^A Minimum tensile strength and yield strength shall be reduced 10 % for cast bars having a cross section, thickness, diameter, or wall of 4 in. (102 mm) or more. The cross sections are the diameter of a round solid, the distance across the flats of a solid hexagon, the thickness of a rectangle, and the wall thickness of a tube.

^B ksi = 1000 psi.

^C See Appendix.

^D Yield strength at 0.2 % offset, min^A, ksi^B, MPa^C.

^E Copper Alloy UNS No. C95520 used only in the quench-hardened and tempered (TQ30) condition.

^F As cast or temper annealed.

8. Dimensions and Permissible Variations

8.1 Allowance for finishing over maximum outside dimension and under inside dimension of round tubes to be machined shall be as shown in Table 3. Allowances for finishing the outside diameter of rounds and distance between parallel surfaces of bars to be machined shall be as shown in Table 4. Table 3 and Table 4 are to be used in conjunction with Tolerance Table 6 and Table 5, respectively.

8.2 Concentricity:

8.2.1 *All Alloys Except as Noted in 8.2.2*—The outside periphery of continuously cast tubing shall be concentric with the bore within a permissible variation of 2 % of the nominal wall thickness over ¼ in. (6.35 mm). With wall thicknesses ¼ in. and less, permissible variations in concentricity shall be subject to agreement between the purchaser and the manufacturer.

TABLE 10 Chemical Requirements

Composition, % max, except as indicated

Copper Alloy UNS No.	Major Elements									Residual Elements						
	Copper	Tin	Lead	Zinc	Iron	Nickel Including Cobalt	Aluminum	Manganese	Iron	Antimony	Nickel Including Cobalt	Sulfur	Phosphorus	Aluminum	Manganese	Silicon
C83600	84.0–86.0	4.0–6.0	4.0–6.0	4.0–6.0	...	1.0	0.30	0.25	...	0.08	1.5	0.005	...	0.005
C83800	82.0–83.8	3.3–4.2	5.0–7.0	5.0–8.0	...	1.0	0.30	0.25	...	0.08	1.5	0.005	...	0.005
C84200	78.0–82.0	4.0–6.0	2.0–3.0	10.0–16.0	...	0.8	0.40	0.25	...	0.08	1.5	0.005	...	0.005
C84400	78.0–82.0	2.3–3.5	6.0–8.0	7.0–10.0	...	1.0	0.40	0.25	...	0.08	1.5	0.005	...	0.005
C84800	75.0–77.0	2.0–3.0	5.5–7.0	13.0–17.0	...	1.0	0.40	0.25	...	0.08	1.5	0.005	...	0.005
C85700	58.0–64.0	0.50–1.5	0.8–1.5	32.0–40.0	0.7	...	1.0	0.55	...	0.05
C86200	60.0–66.0	0.20	0.20	22.0–28.0	2.0–4.0	...	3.0–4.9	2.5–5.0	1.0
C86300	60.0–66.0	0.20	0.20	22.0–28.0	2.0–4.0	...	5.0–7.5	2.5–5.0	1.0
C86500	55.0–60.0	1.0	0.40	36.0–42.0	0.40–2.0	...	0.50–1.5	0.10–1.5	1.0
C89320 ^A	87.0–91.0	5.0–7.0	0.09	1.0	...	1.0	0.20	0.35	...	0.08	0.30	0.005	...	0.005
C90300	86.0–89.0	7.5–9.0	0.30	3.0–5.0	...	1.0	0.20	0.20	...	0.05	1.5	0.005	...	0.005
C90500	86.0–89.0	9.0–11.0	0.30	1.0–3.0	...	1.0	0.20	0.20	...	0.05	1.5	0.005	...	0.005
C90700	88.0–90.0	10.0–12.0	0.50	0.50	...	0.50	0.15	0.20	...	0.05	1.5	0.005	...	0.005
C91000	84.0–86.0	14.0–16.0	0.20	1.5	...	0.8	0.10	0.20	...	0.05	1.5	0.005	...	0.005
C91300	79.0–82.0	18.0–20.0	0.25	0.25	...	0.50	0.25	0.20	...	0.05	1.5	0.005	...	0.005
C92200	86.0–90.0	5.5–6.5	1.0–2.0	3.0–5.0	...	1.0	0.25	0.25	...	0.05	1.5	0.005	...	0.005
C92300	85.0–89.0	7.5–9.0	0.3–1.0	2.5–5.0	...	1.0	0.25	0.25	...	0.05	1.5	0.005	...	0.005
C92500	85.0–88.0	10.0–12.0	1.0–1.5	0.50	...	0.8–1.5	0.30	0.25	...	0.05	1.5	0.005	...	0.005
C92700	86.0–89.0	9.0–11.0	1.0–2.5	0.7	...	1.0	0.20	0.25	...	0.05	1.5	0.005	...	0.005
C92800	78.0–82.0	15.0–17.0	4.0–6.0	0.8	...	0.8	0.20	0.25	...	0.05	1.5	0.005	...	0.005
C92900	82.0–86.0	9.0–11.0	2.0–3.2	0.25	...	2.8–4.0	0.20	0.25	...	0.05	1.5	0.005	...	0.005
C93200	81.0–85.0	6.3–7.5	6.0–8.0	2.0–4.0	...	1.0	0.20	0.35	...	0.05	1.5	0.005	...	0.005
C93400	82.0–85.0	7.0–9.0	7.0–9.0	0.8	...	1.0	0.20	0.50	...	0.08	1.5	0.005	...	0.005
C93500	83.0–86.0	4.3–6.0	8.0–10.0	2.0	...	1.0	0.20	0.30	...	0.08	1.5	0.005	...	0.005
C93600	79.0–83.0	6.0–8.0	11.0–13.0	1.0	...	1.0	0.20	0.55	...	0.08	1.5	0.005	...	0.005
C93700	78.0–82.0	9.0–11.0	8.0–11.0	0.8	...	1.0	0.15	0.50	...	0.08	1.5	0.005	...	0.005
C93800	75.0–79.0	6.3–7.5	13.0–16.0	0.8	...	1.0	0.15	0.80	...	0.08	1.5	0.005	...	0.005
C93900	76.5–79.5	5.0–7.0	14.0–18.0	1.5	...	0.8	0.40	0.50	...	0.08	1.5	0.005	...	0.005
C94000	69.0–72.0	12.0–14.0	14.0–16.0	0.50	...	0.5–1.0	0.25	0.50	...	0.08	1.5	0.005	...	0.005
C94100	72.0–79.0	4.5–6.5	18.0–22.0	1.0	...	1.0	0.25	0.8	...	0.08	1.5	0.005	...	0.005
C94300	67.0–72.0	4.5–6.0	23.0–27.0	0.8	...	1.0	0.25	0.8	...	0.08	1.5	0.005	...	0.005
C94700 ^B	85.0–90.0	4.5–6.0	0.10	1.0–2.5	...	4.5–6.0	0.25	0.15	...	0.05	0.05	0.005	0.20	0.005
C94800	84.0–89.0	4.5–6.0	0.3–1.0	1.0–2.5	...	4.5–6.0	0.25	0.15	...	0.05	0.05	0.005	0.20	0.005
C95200	86.0 min	2.5–4.0	...	8.5–9.5
C95300	86.0 min	0.8–1.5	...	9.0–11.0
C95400	83.0 min	3.0–5.0	1.5	10.0–11.5	0.50
C95410	83.0 min	3.0–5.0	1.5–2.5	10.0–11.5	0.50
C95500	78.0 min	3.0–5.0	3.0–5.5	10.0–11.5	3.5
C95520 ^C	74.5 min	0.25	0.03	0.30	4.0–5.5	4.2–6.0	10.5–11.5	1.5
C95700	71.0 min	...	0.03	...	2.0–4.0	1.5–3.0	7.0–8.0	11.0–14.0	0.10
C95800 ^D	79.0 min	...	0.03	...	3.5–4.5	4.0–5.0	8.5–9.5	0.8–1.5	0.10
C95900	remainder	3.0–5.0	0.5	12.0–13.5	1.5
C96400 ^E	65.0–69.0	...	0.03	...	0.25–1.50	28.0–32.0	...	1.5	0.02	0.02
C96900 ^F	remainder	5.8–8.5	0.02	11.0–15.5	...	0.05–0.40	0.5
C97300	53.0–58.0	1.5–3.0	8.0–11.0	17.0–25.0	...	11.0–14.0	1.5	0.35	...	0.08	0.05	0.005	0.50	0.15
C97600	63.0–67.0	3.4–4.5	3.0–5.0	3.0–9.0	...	19.0–21.5	1.5	0.25	...	0.08	0.05	0.005	1.0	0.15
C97800	64.0–67.0	4.0–5.5	1.0–2.5	1.0–4.0	...	24.0–27.0	1.5	0.20	...	0.08	0.05	0.005	1.0	0.15
C99500 ^G	remainder	...	0.25	0.5–2.5	3.0–5.0	3.5–5.5	0.5–2.0	0.5

^A Bismuth 4.0–6.0

^B It is possible that the mechanical requirements of Copper Alloy UNS No. C94700 in the heat-treated condition will not be attained if the lead content exceeds 0.01 %.

^C Chromium content shall be 0.05 max, cobalt 0.20 max, and silicon 0.15 max.

^D Iron content shall not exceed nickel content. Other major element chemical requirements: Silicon 0.10 % max.

^E Chemical requirements for other elements: Sulfur 0.02 % max (major), carbon 0.15 % max (residual), and niobium 0.5–1.5 (major).

^F Magnesium 0.15 max (major), silicon 0.30 max (residual), niobium 0.10 max (residual).

^G Silicon 0.5–2.0

8.2.2 *Copper Alloy UNS Nos. C86200, C86300, C86400, C95200, C95300, C95400, C95410, C95500, C95520, C95800, C95900, and C96400*—The outside periphery of continuously cast tubing shall be concentric with the bore within a permissible variation of 4 % of the nominal wall thickness.

8.3 *Diameter Tolerances for Continuously Cast Rod and Bar*—See Table 5.

8.4 *Tolerances of Average Diameter for Continuously Cast Tube (Round only)*—See Table 6.

8.5 *Roundness*—For continuously cast tubing in straight lengths, the roundness tolerances shall be as shown in Table 7.

8.6 *Dimensional Tolerances for All Other Shapes (not Covered by 7.1 or 8.2)*—See Table 8.

8.7 *Straightness Tolerances for Continuously Cast Rod, Tube, Bars, and Shapes*—See Table 12.

9. Casting Repair

9.1 Continuous castings shall not be mechanically repaired, plugged, or burned in.

TABLE 11 Sum of All Named Elements Analyzed

Copper Alloy UNS No.	Copper Plus Named Elements, %min	Copper Alloy UNS No.	Copper Plus Named Elements, %min
C83600	99.3	C93700	99.0
C83800	99.3	C93800	98.9
C84200	99.3	C93900	98.9
C84400	99.3	C94000	98.7
C84800	99.3	C94100	98.7
C85700	98.7	C94300	99.0
C86200	99.0	C94700	99.3
C86300	99.0	C94800	99.3
C86500	99.0	C95200	99.0
C90300	99.4	C95300	99.0
C90500	99.7	C95400	99.5
C90700	99.4	C95410	99.5
C91000	99.4	C95500	99.5
C91300	99.4	C95520	99.5
C92200	99.3	C95700	99.5
C92300	99.3	C95800	99.5
C92500	99.3	C95900	99.5
C92700	99.3	C96400	99.5
C92800	99.3	C96900	99.5
C92900	99.3	C97300	99.0
C93200	99.2	C97600	99.7
C93400	99.2	C97800	99.6
C93500	99.4	C99500	99.7

TABLE 12 Straightness Tolerances

Product	Length, ^A ft (m)	Maximum Curvature ^B (Depth of Arc), in. (mm)
Round rod or tube	up to 10 (3.05)	1/4 (6.4) in any 5-ft (1.52-m) portion
	10 (3.05) and over	1/2 (13) in any 10-ft (3.05-m) portion ^A
Bar and shape	any length	1/2 (13) in any 6-ft (1.83-m) portion ^{A,B}

^A Of total length.

^B Applicable to any longitudinal surface or edge.

9.2 Weld repair is permitted for Copper Alloy UNS Nos. C95200, C95300, C95400, C95410, C95500, C95800, and C95900.

9.3 Weld repairs may be made at the manufacturer's discretion provided each excavation does not exceed 20 % of the casting section or wall thickness or 4 % of the casting surface area.

9.4 Excavations that exceed those described in 8.2 may be made at the manufacturer's discretion except that when specified in the purchase order (4.1.12) the weld procedure shall be approved by the purchaser and the following records shall be maintained:

9.4.1 A sketch or drawing showing the dimensions, depth, and location of excavations,

9.4.2 Post-weld heat treatment, when applicable,

9.4.3 Weld repair inspection results,

9.4.4 Casting identification number,

9.4.5 Weld procedure identification number,

9.4.6 Welder identification, and

9.4.7 Name of inspector.

9.5 The castings shall not be impregnated without approval of the purchaser.

9.6 Weld repair of other alloys in this specification is not permitted without approval by the purchaser.

10. General Requirements

10.1 The following sections of Specification B 824 form a

part of this specification.

10.1.1 Terminology (Section 3),

10.1.2 Other Requirements (Section 6),

10.1.3 Workmanship, Finish, and Appearance (Section 8),

10.1.4 Number of Tests and Retests (Section 10),

10.1.5 Specimen Preparation (Section 11),

10.1.6 Test Methods (Section 12),

10.1.7 Significance of Numerical Limits (Section 13),

10.1.8 Inspection (Section 14),

10.1.9 Rejection and Rehearing (Section 15),

10.1.10 Certification (Section 16),

10.1.11 Test Report (Section 17),

10.1.12 Product Marking (Section 18),

10.1.13 Packaging and Package Marking (Section 19),

10.1.14 Supplementary Requirements.

11. Sampling

11.1 Unless otherwise specified, a lot shall consist of castings of the same composition and same cross-sectional dimensions, produced during the continuous operation of one casting machine, and submitted for inspection at one time.

11.2 A sample for chemical analysis shall be taken from each lot at each interval of 2000 lb (910 kg) of continuous production of the lot. When castings are produced from alloy ingots of known composition, the sampling interval may be raised to one sample for each 4000 lb (1810 kg) of continuous production of the lot.

11.3 When mechanical testing is specified by the purchaser in the purchase order one sample for tension testing shall be taken from each lot. This sample may be taken before mechanical straightening. Test coupons shall be positively identified with the castings they represent. Where castings are heat treated, test coupons shall be heat treated with the castings they represent.

11.4 When Copper Alloy UNS No. C95200 is specified for ASME boiler and pressure vessel requirement, a sample from each 2000-lb interval or continuous casting shall be tested. Each continuous cast bar from which the test bar was taken shall be identified should retesting be required. If all of the test bars from the initial sampling meet the requirements, the lot shall be acceptable.

11.4.1 The fractured bars shall be retained for chemical verification.

11.5 Tension test bar specimens shall be taken from continuous castings in accordance with Fig. 6 of Practice B 208.

12. Test Methods

12.1 Analytical chemical methods are given in Specification B 824 (Section 12).

12.2 Brinell Hardness Reading shall be taken on the grip end of the tension test bar and shall be made in accordance with Test Method E 10 with the exception that a 3000-kg load shall be used.

12.3 Rockwell Hardness Reading shall be taken on the grip end of the tension test bar and shall be made in accordance with Test Methods E 18.

13. Product Marking

13.1 At the request of the purchaser castings shall be marked with the alloy number.

14. Keywords

14.1 continuous castings; copper alloy castings; copper-base alloy castings

APPENDIX**(Nonmandatory Information)****X1. METRIC EQUIVALENTS**

X1.1 The SI unit for strength properties now shown is in accordance with the International System of Units (SI). The derived SI unit for force is the newton (N), which is defined as that force which when applied to a body having a mass of one kilogram gives it an acceleration of one metre per second squared ($N = \text{kg}\cdot\text{m}/\text{s}^2$). The derived SI unit for pressure or

stress is the newton per square metre (N/m^2), which has been named the pascal (Pa) by the General Conference on Weights and Measures. Since $1 \text{ ksi} = 6\,894\,757 \text{ Pa}$ the metric equivalents are expressed as megapascal (MPa), which is the same as MN/m^2 and N/mm^2 .

SUMMARY OF CHANGES

This section identifies principle changes to this specification since the last issue.

1. Section 10 was rewritten to list the sections of Specification B 824 which apply to this specification.
2. Section 3 was rewritten.
3. The second sentence of paragraph 5.2 was revised to provide for “analysis required.”

4. Paragraphs 6.2 and 11.3 were revised to eliminate an existing conflict.

5. New Section 7 was added combining paragraph 9.4 and Section 12 and adding other ASME requirements.

6. Paragraph 12.1 was added.

7. Copper Alloy UNS Nos. C69600 and C99500 were added.

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 100 Barr Harbor Drive, West Conshohocken, PA 19428.